



UV Light Curing Lens-Bonding and Fiber Optic Adhesives


Dymax OP Series of high-strength, low-stress optical assembly adhesives cures in seconds upon exposure to UV/Visible light. Dymax optical adhesives are single component, low outgassing, low shrinkage, and have a gap filling capability to 6.4 mm [0.25 in] or more. High performance fiber optic adhesives minimize movement of parts during cure and thermal excursions. By combining new ingredients in novel ways, Dymax fiber optic adhesives offer improved durability and reliability along with superior optical transmission, low outgassing, and complete cure in seconds.



VCSEL Potting



Fiber Optic Bundling



Lens Curing



Lens Positioning

Features and Benefits

- Low to no movement during cure and thermal excursions (from -50°C to 200°C)
- Exceptionally low shrinkage to 0.1%
- Low to high glass transition points (T_g)
- A range of refractive indices from 1.40-1.58
- Low outgassing to 10^{-6} grams/gram
- Superior optical transmission
- Single component, no mixing required
- Gap filling to 6.4 mm [0.25 in] or more
- Environmentally resistant
- No VOCs
- Low odor

Dymax offers a complete line of high-performance light-curable adhesives and light-curing equipment for optical applications for the industrial, commercial, medical, military, aerospace, and electro-optical markets. Over 30 years of experience in this industry has led to a superior product line of adhesives, applicators, and UV light-curing sources.

The First Adhesives Developed for High-Speed Fiber Optic Assembly






Easily automate production of products such as lenses, fiber optics, prisms, mirrors, and other assemblies. Dymax OP Series UV light-curable fiber optic adhesives cure in seconds, have unlimited pot life, long shelf life, and are not frozen.

[Want to learn more?](#)


Visit www.dymax.com to register to download the white paper "*Advances in Light-Curing Adhesives*"

Product Selector Guide

Products	Description	Linear Shrinkage	Refractive Index (cured)	Viscosity (cP)	Durometer Hardness	Adhesion			
						D=Rigid A=Elastic OO=Soft	Ceramic	Glass	Metal
OP-24-Rev. B (501-E)	Clear; Multi-Cure® (UV/light/heat/activator); tack and bond with UV, heat, or activator where light won't reach; lens mounting	3.7%	1.502	800	D80		✓	✓	✓
OP-29	Clear; UV light cure; doublet bonding; lens mounting; fiber optic splicing	2.8%	1.504	2,500	D60		✓	✓	✓
OP-29-Gel	Clear; UV light cure; doublet bonding; lens mounting; fiber optic splicing	2.8%	1.504	110,000	D60		✓	✓	✓
OP-67-LS	White/opaque; UV/Visible light cure; low shrinkage; low outgassing for alignment stability; doublet bonding	<0.1%	N/A	135,000	D80	✓	✓	✓	✓
OP-4-20632	Clear; tenacious adhesion to glass and metal; low shrink on cure; T _g increases with heat exposure; moisture resistant; resists yellowing	<0.2%	1.554	500	D75	✓			✓
OP-4-20632-Gel	Clear; tenacious adhesion to glass and metal; low shrink on cure; T _g increases with heat exposure; moisture resistant; resists yellowing	<0.2%	1.554	50,000	D75	✓			✓



High T_g's of new UV's compared to those of epoxy



Minimal movement with temperature change means improved durability

Product Selector Guide

Products	T _g Glass Transition Temperature °C (By TMA)	Outgassing ASTM E595-77 85°C at 5x10 ⁻⁶ torr for 24 Hours TWL ¹ /CVCm ²	Tensile Bar Strength ASTM D638			Bond Strength Compressive Shear		
			Tensile (psi [MPa])	Modulus of Elasticity (psi [MPa])	Elongation	Glass to Glass (psi [MPa])	Steel to Glass (psi [MPa])	Steel to Steel (psi [MPa])
OP-24-Rev. B (501-E)	79 ^{uh} 92 ^u	5.2% / <0.04%	5,200 [36]	320,000 [2,206]	35%	4,000 [28]	5,000 [34]	2,900 [20]
OP-29	64 ^{uh} 67 ^u	3.66% / 0.25%	5,000 [34]	35,000 [241]	120%	2,300 [16]	1,700 [12]	N/A
OP-29-Gel	56 ^{uh} 58 ^u	3.66% / 0.25%	4,700 [32]	35,000 [241]	120%	2,300 [16]	1,700 [12]	N/A
OP-67-LS	86 ^{uh} 125 ^u	nm	4,000 [28]	83,000 [570]	6.5%	nm	nm	N/A
OP-4-20632	78 ^{uh} 87 ^u	nm	8,900 [61]	800,000 [5,500]	2%	2,200 [15]	525 [3.6]	N/A
OP-4-20632-Gel	78 ^{uh} 87 ^u	nm	8,900 [61]	800,000 [5,500]	2%	2,200 [15]	525 [3.6]	N/A

^{uh}=UV plus heat (75 minutes @ 110°C) cure

^u= UV only cure

nm = not measured




Diode Curing




Lens Bonding




Lens Laminating



Prism Curing



Dymax OP series adhesives show superior optical transmission




Transmission curves from graph on left expanded from 70% level and higher

UV Light-Curing Systems for Optical Adhesives


Tired of short storage and shelf life, of mixing two components, and waiting for adhesives to thaw? Dymax UV light-curing adhesives and systems cure completely in seconds. **Make automation easier!**




Dymax BlueWave® 200 UV-Curing Spot Lamp with patented intensity adjustment feature provides high-intensity UV/Visible light in a concentrated area. Ideal for integration with automated equipment and multiple-output lightguides. **CE Marked.**



Dymax BlueWave® 75 UV-Curing Spot Lamp Shown with single lightguide features a patented intensity adjustment feature and an auto-switching power supply to neutralize the effects of variations in line voltage. **CE Marked.**



Dymax 2000 UV Curing Flood Lamp System Shown with Light Shield protective enclosure and manual shutter. Ideal for single component or batch curing processes requiring moderate intensity and a 20 cm x 20 cm cure area. **CE Marked**



Dymax 5000 UV Curing Flood Lamp System Shown with Light Shield protective enclosure and ZIP™ shutter. Ideal for single component or batch curing processes requiring moderate intensity and a 12.7 cm x 12.7 cm cure area. **CE Marked**

© 2001-2012 Dymax Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A. The data contained in this bulletin is of a general nature and is based on laboratory test conditions. Dymax Europe GmbH does not warrant the data contained in this bulletin. Any warranty applicable to products, its application and use is strictly limited to that contained in Dymax Europe GmbH's General Terms and Conditions of Sale published on our homepage http://www.dymax.com/de/pdf/dymax_europe_general_terms_and_conditions_of_sale.pdf. Dymax Europe GmbH does not assume any responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this bulletin shall act as a representation that the product use or application will not infringe a patent owned by someone other than Dymax Corporation or act as a grant of license under any Dymax Corporation Patent. Dymax Europe GmbH recommends that each user adequately test its proposed use and application of the products before actual repetitive use, using the data contained in this bulletin as a general guide. LIT208EU Rev. 1/16/2012

Dymax Corporation
860.482.1010
info@dymax.com
www.dymax.com

Dymax Europe GmbH
+49 (0) 611.962.7900
info_de@dymax.com
www.dymax.de

Dymax UV Adhesives & Equipment (Shenzhen) Co Ltd
+86.755.83485759
dymaxasia@dymax.com
www.dymax.com.cn

Dymax Asia (Hong Kong) Ltd
+852.2460.7038
dymaxasia@dymax.com
www.dymax.com.cn

Dymax Korea LLC
82.2.784.3434
info@dymax.kr
www.dymax.co.kr

