

Methods of Reworking/Repairing DYMAX 984 Series Conformal Coatings

Rework and repair of DYMAX conformal coatings have proven successful using three methods:

Heat Removal: Use of a pencil-point hot-air gun will direct a concentrated flow of intense heat (400° - 425°F) to the work site. In some cases, a solder gun can prove a high enough temperature when applied directly to the work area. These methods are especially useful when the surrounding area contains heat sensitive components. When heat sensitivity is not a factor, a heat gun can be used to heat the general area.

Chemical Removal: Several companies manufacture materials which dissolve/attack conformal coatings. Below is a list of materials which have been shown to be effective.

PRODUCT	COMPANY	TELEPHONE NUMBER
Ultra-V-Strip	Adhesive Engineering and Supply	603-474-3070
Fine-L-Kote Remover	Tech-Spray	806-372-8523
Jasco Epoxy Remover	Jasco, Inc.	415-968-6005
Dynasolve 100, 210 Uresolve 411	Dynaloy, Inc.	800-669-5709

Removal by Abrasion: Comco, Inc. manufactures the Micro-Blaster System which removes coatings using a pressurized abrasive. (Telephone Number: 818-841-5500)

Since each application presents its own unique set of circumstances, the above information is to be used as a guideline. Please contact DYMAX Applications Engineering if you need assistance.

© 1997-2010 DYMAX Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by DYMAX Corporation, U.S.A.

The data contained in this bulletin is of a general nature and is based on laboratory test conditions. DYMAX does not warrant the data contained in this bulletin. Any warranty applicable to the product, its application and use is strictly limited to that contained in DYMAX's standard Conditions of Sale. DYMAX does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this bulletin shall act as a representation that the product use or application will not infringe a patent owned by someone other than DYMAX or act as a grant of license under any DYMAX Corporation Patent. DYMAX recommends that each user adequately test its proposed use and application before actual repetitive use, using the data contained in this bulletin as a general guide.

Lit144 03/01/1997